

# **UTP 65**

Stand	ards	:
-------	------	---

Material-No.	:	~ 1.4337
DIN 8555	:	~ E 9-UM-250-KR
EN 1600	:	~ E 29 9 R 32
EN 14700	:	E I.II

Rutile coated austenitic-ferriticspecial stick electrode with optimal welding and mechanical properties

# **Application field**

**UTP 65** is particularly suitable for joinings on hardly weldable steels, when highest demands on the welding seam are made. High crack resistance when joining parent metals of difficult weldability, such as austenitic and ferritic steels, high-manganese steels with alloyed and non-alloyed steels, heat-treatable and tool steels. As cushion layer on these materials it is also ideally suited. UTP 65 finds a variety of applications in the repair and maintenance of machine and drive components as well as in tool repairing.

## Welding properties and special properties of the weld metal

**UTP 65** is very easily weldable with a smooth and stable arc, homogeneous, finely rippled bead appearance and gives very good slag removal, self-lifting in parts. The austenitic-ferritic weld deposit has highest strength values and high crack resistance. Workhardening, creep resistant and stainless.

## Hardness of the pure weld metal

approx. 240 HB

#### Mechanical properties of the weld metal

Yield strength	Tensile strength R	Elongation A
MPa	MPa	%
> 620	> 800	> 22

#### Weld metal analysis in %

С	Si	Mn	Cr	Ni	Fe
0,1	١,0	١,0	29,0	9,0	balance

#### Welding instruction

Clean welding area thoroughly. Pre-heating of thick-walled ferritic parts to  $150 - 250^{\circ}$  C. Keep the arc short up to medium-long. Apply string beads with little weaving. Hold stick electrode as vertically as possible. Redry stick electrodes that have got damp for 2 h / 120 - 200° C.

Current type DC (+) / AC

Welding positions



## Availability / Current adjustment

Stick electrodes	Ø mm x L	1,5 x 250*	2,0 x 250	2,5 x 250	3,2 x 350	4,0 x 350	5,0 x 350
Amperage	А	35 - 50	45 - 65	60 - 80	80 - 130	110 - 150	120 - 200

\* available on request

Approvals DB (No. 82.138.01)

Официальный дистрибьютор ЗАО «Ресурс» т/ф 8(383) 363-26-24, 291-93-02 630020 Россия г.Новосибирс ул.Объединения д.9 e-mail: resurszao@yandex.ru